Mayfair Slabs

SCAN HERE

Granite aggregate paving slabs.

Mayfair slabs have a sophisticated, modern feel. Manufactured with natural granite aggregates, Mayfair slabs have a hard-wearing, durable surface and come in four natural colours.

- Manufactured with natural granite aggregates
- Superb hard-wearing granite surface
- Vibrant long-lasting colours
- Creates a striking, contemporary look

PrimeTop®

TGA	Steps	Pedestrian Use	Light Traffic	Commercial Traffic	BIM Level 2
Textured Granite Aggregate					
Finish	**Also available as**	Refer to relevant guidance in BS 7533			



600 x 600mm

600 x 400mm

450 x 450mm

400 x 400mm

Sizes

50mm
40mm
35mm

Depths

Mayfair Slabs



Specification

PrimeTop®

Product type	Concrete Paving Slab
Manufactured to	BS EN 1339:2003
Surface Layer	Hard-wearing surface layer with a minimum of 4mm and >390kgs/m^3 cement
Chamfer	Chamfered
Granite content	Not less than 57% of granite aggregate in surface layer for Silver and Graphite; Not less than 46% of granite aggregate in surface layer for Sandstone & Oat
Efflorescence	Minimum 12 hour vapour curing to significantly reduce the possibility of efflorescence
Bending Strength	**Less than 50mm deep** Characteristic tensile splitting strength not less than 3.6 MPa **50mm or greater** Characteristic tensile splitting strength of >5MPa (Class 3)
Slip/Skid Resistance	Mean polished skid resistance value (PSRV) >45 Mean unpolished skid resistance value (USRV) >45
Installed to	BS 7533-102:2025
NSS	**Plus** Q25 315 **Create** 45-20-64/395
Tolerances on Dimensions (mm)	Length ±3mm, width ±3mm, thickness ±3mm
Abrasion Resistance (mm)	≤ 23mm (Wide Wheel Abrasion Test) Class 3
Durability (Freeze-thaw)	≤ 1.0 kg/m^2 as a mean with no individual value > 1.5 kg/m^2 Class 3
External Fire Performance	Deemed to satisfy when used for roofing
Reaction to fire	Class A1
Applications	Refer to the relevant part of BS 7533 for the correct sub-base design and the most suitable product size for your application. Available from www.bsigroup.com
Energy used	100% renewable energy
Water used	100% from our rainwater harvesting system and groundwater bore hole
Recycled content	Not less than 6%
Carbon Footprint	**EPD Verified** *(2020)* **400x400x40mm** 10.43kgCo^2e/m^2 **450x400x35mm** 8.96kgCo^2e/m^2 **450x450x50mm** 12.51kgCo^2e/m^2 **600x400x50mm** 13.19kgCo^2e/m^2 **600x600x50mm** 12.54kgCo^2e/m^2
Recyclable	100% of this product can be recycled
Manufacturing & Delivery	From one location within the UK
breeam rating www.**bre**.co.uk	**A**, according to the Green Guide to Specification, 4th Edition 2009. **A+**, can be achieved by using a recycled sub-base.

Tobermore products are manufactured in accordance with an accredited ISO 9001:2015 Quality Management. Manufacturing facilities are accredited to ISO14001:2015 Environmental Management. The company publish environmental labels and declarations in accordance with BES 6001.

Contact Us
GB: 0844 800 5736
NI: 028 7964 2411
ROI: 048 7964 2411

Email
technical@tobermore.co.uk
sales@tobermore.co.uk

Mayfair Slabs



Silver



Graphite



Oat



Stock

product	size (mm)	edge	colours available	in stock	no. per m²	no. per pack	no. per pallet	weight kg per pack GB	weight kg per pack NI/ROI
Mayfair Slabs BIM	600 x 600 x 50	Chamfered	Graphite, Oat, Silver	YES	2.78	20	20	850	840
	600 x 400 x 50	Chamfered	Graphite, Oat, Silver	YES	4.16	52	52	1466	1466
	450 x 450 x 50	Chamfered	Graphite, Oat, Silver	YES	4.94	20	80	478	488
	450 x 450 x 35	Chamfered	Graphite, Oat, Silver	YES	4.94	30	60	535	525
	400 x 400 x 40	Chamfered	Graphite, Oat	YES	6.25	25	100	392	382
			Silver			90	90	1382	1382

BIM - This product is available to download from our website in BIM Level 2 format.

Contact Us
GB: 0844 800 5736
NI: 028 7964 2411
ROI: 048 7964 2411

Email
technical@tobermore.co.uk
sales@tobermore.co.uk