

# PRODUCT DATA SHEET

## Sikafloor® ProSeal W

### WATER DISPERSED CURING AND SEALING COMPOUND FOR CONCRETE FLOORS

#### PRODUCT DESCRIPTION

Sikafloor® ProSeal W is a one part water dispersed acrylic emulsion to cure, harden and seal fresh or hardened concrete.

#### USES

Sikafloor® ProSeal W installation works to be carried out only by Sika Approved Contractors. Please observe information given by Product Data Sheets.

Sikafloor® ProSeal W is used for optimum curing and sealing of fresh concrete floors and structures.

- Curing compound in order to limit surface drying and cracking
- Provides curing and sealing for Sikafloor® dry shake hardeners
- Anti-dust treatment and improvement of the abrasion resistance of existing concrete surfaces
- Suitable for exterior and interior application

#### CHARACTERISTICS / ADVANTAGES

- Water dispersion
- Suitable for indoor use where solvent-based products cannot be applied because of health and safety regulations
- Helps control dusting for both new and existing concrete floor surfaces
- Effectively cures and seals concrete surfaces in a single, economic operation
- Very low yellowing
- Easy application by spray or roller

#### APPROVALS / STANDARDS

Tested for water retention according to ASTM C-156 for curing liquids type 1, class Conforms to the requirements of EN 13813 SR - B 1.5. Epoxy textured roller and seal coat according to EN 13813:2002, DoP 02 08 03 04 005 0 000003 1029 and provided with the CE-mark

#### PRODUCT INFORMATION

Chemical Base	Water dispersed acrylic emulsion.
Packaging	25 l cans and 200 l drums
Appearance / Colour	White liquid, clear when cured.
Shelf Life	12 months from date of production
Storage Conditions	stored properly in original, unopened and undamaged sealed containers, in dry conditions at temperatures between +5 °C and +30 °C. Protect from frost.
Density	~1.0 kg/l (at +20 °C)
Solid content by weight	~16 %

#### SYSTEM INFORMATION

#### APPLICATION INFORMATION

<b>Consumption</b>	0.1–0.2 l/m <sup>2</sup> /coat Requirements of relevant local standards and guidelines apply. This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage, etc.												
<b>Ambient Air Temperature</b>	+10 °C min. / +30 °C max.												
<b>Relative Air Humidity</b>	80 % max.												
<b>Dew Point</b>	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.												
<b>Substrate Temperature</b>	+10 °C min. / +30 °C max.												
<b>Curing Time</b>	<table border="1"> <thead> <tr> <th>Substrate temperature</th> <th>Foot traffic</th> <th>Full cure</th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~16 hours</td> <td>~24 hours</td> </tr> <tr> <td>+20 °C</td> <td>~8 hours</td> <td>~20 hours</td> </tr> <tr> <td>+30 °C</td> <td>~6 hours</td> <td>~16 hours</td> </tr> </tbody> </table> <p>Full cure times are approximate and will be affected by changing substrate and ambient conditions</p>	Substrate temperature	Foot traffic	Full cure	+10 °C	~16 hours	~24 hours	+20 °C	~8 hours	~20 hours	+30 °C	~6 hours	~16 hours
Substrate temperature	Foot traffic	Full cure											
+10 °C	~16 hours	~24 hours											
+20 °C	~8 hours	~20 hours											
+30 °C	~6 hours	~16 hours											
<b>Waiting Time / Overcoating</b>	<p>Allow previous coats to become tack free before applying additional coats.</p> <table border="1"> <thead> <tr> <th>Substrate temperature</th> <th>Time</th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~90 minutes</td> </tr> <tr> <td>+20 °C</td> <td>~45 minutes</td> </tr> <tr> <td>+30 °C</td> <td>~40 minutes</td> </tr> </tbody> </table> <p>Times are approximate and will be affected by changing substrate and ambient conditions, particularly temperature and relative humidity.</p>	Substrate temperature	Time	+10 °C	~90 minutes	+20 °C	~45 minutes	+30 °C	~40 minutes				
Substrate temperature	Time												
+10 °C	~90 minutes												
+20 °C	~45 minutes												
+30 °C	~40 minutes												

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

#### Fresh concrete

Surface must be free of bleed water and of sufficient strength to withstand finishing operations. The concrete must be prepared by suitable power or manual floating / tamping techniques.

#### Hardened / old concrete

Surfaces must be sound, open textured, clean, free from frost, laitance, surface water, oil, grease, coatings, all loosely adhering particles and other surface contaminants. The substrate must be prepared by suitable mechanical preparation techniques such as high-pressure water or abrasive blast cleaning equipment. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum. If in doubt apply a test area first.

### MIXING

Sikafloor® ProSeal W is supplied ready for use. Stir thoroughly with an electric stirrer with low speed (~300 rpm) for 2 minutes before use.

### APPLICATION

For fresh concrete, apply immediately after finishing techniques have been completed.

For dry shaked topped concrete, apply immediately after completion of the power floating operation. Apply in a continuous even film by low-pressure spray unit. The suitability of spraying equipment must be confirmed by trials.

Application also possible by brush or roller. To achieve the highest visual aesthetics and performance, a second coat is recommended. Wait for first coat to dry tack free before applying a second coat. (see waiting time / overcoating)

### CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be removed mechanically.

### MAINTENANCE

#### CLEANING

To maintain the appearance of the floor after application, Sikafloor® ProSeal W must have all spillages removed immediately and must be regularly cleaned using rotary brushes, mechanical scrubbers, scrubber dryers, high pressure washers, wash and vacuum techniques, etc., using suitable detergents and waxes.

## LIMITATIONS

- In hot weather (above +25 °C) store Sikafloor® ProSeal W in a cool place prior to use.
- In low temperatures (below +10 °C) the product may thicken and be difficult to spray.
- Do not use sprayers which have been used to spray silicones or release agents.
- Do not mix differing formulations of Sika® or other curing membranes.
- Ensure spraying equipment is cleaned thoroughly before use and residues of previous membranes are removed.
- Sikafloor® ProSeal W must be removed prior to the application of a coating system.
- Sikafloor® ProSeal W increases abrasion resistance compared to C25 concrete, but will gradually degrade and be removed by environmental exposure conditions and trafficking.
- Not recommended for concrete floors with metallic dry shake hardeners.
- Do not use outside over white and non absorbent substrates, as some yellowing may be perceptible.

## VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

Local safety regulations must be observed and it advisable to wear PPE when working with this product with particular attention paid to cutting and handling. Transportation Class: The product is not classified as hazardous good for transport. Disposal: The material is recyclable. Disposal must be according to local regulations. Please contact your local Sika sales organisation for more information.

### DIRECTIVE 2004/42/CE - LIMITATION OF EMISSIONS OF VOC

According to the EU Directive 2004/42/CE, the maximum allowed content of VOC (product category IIA / i type wb) is 140 g/l (Limits 2010) for the ready to use product.

The maximum content of Sikafloor® ProSeal W is < 140 g/l VOC for the ready to use product.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA IRELAND LIMITED**  
Ballymun Industrial Estate  
Ballymun  
Dublin 11, Ireland  
Tel: +353 1 862 0709  
Web: [www.sika.ie](http://www.sika.ie)  
Twitter: @SikaIreland



**Product Data Sheet**  
Sikafloor® ProSeal W  
April 2020, Version 01.02  
020815110010000008

SikafloorProSealW-en-IE-(04-2020)-1-2.pdf